

## **TECHNICAL DATA SHEET**

<u>Fully Refined Wax</u> 全精煉石蠟

Properties	Unit	<b>140</b> °F
Melting Point	°F	136 ~ 142
Oil Content	%	0.50
Penetration [mm/10@77°F]		10.0 ~ 15.5
Flash Point	°C	230
Kinematic Viscosity [@212°F]		4.20 ~ 4.90
Color [ ASTM]		+26 ~ +30
Ultraviolet Absorbance		Pass
Specific Gravity		0.76 ~ 0.77

## PACKAGING

5 kg/cake X 6 cake.

CAS No # 8002-74-2

The information herein is believed to be reliable. However no warranty, express or implied is made as to its accuracy or completeness and none is made as to the fitness of this material for any purpose. The manufacturer shall not be liable for damages to person or property resulting from its use. Nothing herein shall be construed as a recommendation for use in violation of any patent. Consult the Material Safety Data Sheet for additional information.

7F-6, No.100, Sec. 1, JiaFeng 11<sup>TH</sup> Rd., ZhuBei City, Hsinchu 30273, Taiwan. TEL: <u>+886 3 657 8782</u> FAX: <u>+886 3 657 8784</u> E-mail: <u>midas@mamc.com.tw</u>